

► Optical & Geometrical Properties for Single Mode Fibers

► Optical & Geometrical Properties for Single Mode Fibers

Parameter		Standard Single Mode Fiber per ITU-T G.652D	Non-zero Dispersion Shifted fiber per ITU-T G.655	Non-zero Dispersion Shifted fiber per ITU-T G.656	Units
		9	8	7	
Attenuation, Loose Tube Cables		Standard	Metro Area	Long Haul	
	@1310nm	≤0.35	-	-	dB/km
	@1550nm	≤0.22	≤0.22	≤0.22	dB/km
	@1625nm	≤0.25	≤0.26	≤0.26	dB/km
Attenuation, Tight Buffer or Semi-Tight Cables					
	@1310nm	≤0.38	-	-	dB/km
	@1550nm	≤0.28	-	-	dB/km
Chromatic Dispersion	between 1260 and 1360nm (O Band)	≤3.5	NA-	-	ps/(nm*km)
	between 1460 and 1530nm (S Band)	-	-	2.0-7.0	ps/(nm*km)
	between 1530 and 1565nm (C Band)	≤18	1.0-10.0	7.0-10.0	ps/(nm*km)
	between 1565 and 1625nm (L Band)	≤22	7.0-12.0	10.0-14.0	ps/(nm*km)
Zero Dispersion Wavelength		1310±11	≤1520	≤1420	nm
Zero Dispersion Slope		0.093	0.093	0.093	ps/(nm ² .km)
Point Discontinuity at 1300nm& 1550nm		0.1	0.1	0.1	dB
Mode Field Diameter	@1300nm	9.3±0.5	-	-	um
	@1550nm	10.4±0.8	8.5±0.6	9.0±0.5	um
Cable Cut-off Wavelength		≤1260	≤1450	≤1310	nm
PMD (Individual fiber)		≤0.2	≤0.2	≤0.2	ps/km ^{1/2}
Cladding Diameter		125±1	125±1	125±1	um
Core/Cladding Concentricity Error		≤0.5	≤0.5	≤0.6	um
Cladding Non-Circularity		≤1.0	≤1.0	≤1.0	%
Coating Non-Circularity		≤6.0	≤6.0	≤6.0	%
Primary Coating Diameter		245±10	245±10	245±10	um
Proof-Test Level		100 (0.7)	100 (0.7)	100 (0.7)	Kpsi/GN/m ²
Fatigue Coefficient		≥20	≥20	≥20	
Temperature Dependence between 0°C ~ +70°C @ 1310 & 1550nm		0.1	0.1	0.1	Db/km

